



**Date** 3/23/2010 **Vessel** \_\_\_\_\_  
**Material** 26A / G2  
**State Pit Number** 49-065  
**Quarry** Cedarville  
**Sample from stockpile at** BAY AGG YARD  
**Pile Location** Loading Face

Sieve Size	Retained Weight	Retained Percent	Cumulative % Retained	Cumulative % Passing	Specification Requirements
2 1/2 "					<b>26A</b>
2 "					
1 1/2 "	0	0.0%	0.0%	100%	
1 1/4 "					
1 "	0	0.0%	0.0%	100%	
3/4 "	0	0.0%	0.0%	100%	100%
1/2 "	17	0.7%	0.7%	99%	95 / 100%
3/8 "	451	18.5%	19.2%	81%	60 / 90%
no. 4	1661	68.1%	87.3%	13%	5 / 30%
no. 8	253	10.4%	97.7%	2%	0 / 12%
no. 16	23	1.0%	98.7%	1%	
no. 30	7	0.3%	99.0%	1%	
no. 50	2	0.1%	99.0%	1%	
no. 100	0	0.0%	99.0%	1%	
no. 200	0	0.0%	99.0%	1%	
pan	6	0.3%	99.3%	1%	
LBW	17	0.7%			3% Max
<b>TOTAL:</b>	<b>2437.20</b>	<b>99.30%</b>			

**LOSS BY WASH**

**1.23%**

**LBW MAX**

**3**

Initial Weight 2437.2 g  
 Weight after Washing 2407.2 g  
 Loss by Washing 30 g

Accepted X

Rejected \_\_\_\_\_

**MOISTURE**

**1.00%**

Initial Weight 2461.8 g  
 Dry Weight 2437.2 g  
 Moisture 24.6 g

Tested By \_\_\_\_\_

L. Philippi  
 Michigan Certified Aggregate Technician  
 Cert # 101992-0213