



AGGREGATE, INC.

411 Tiernan Rd. • P.O. Box 1067 • Bay City, MI • 48706 • (989) 667-5990 • Fax (989) 667-5991

Date 3/4/2010 B Vessel
 Material 31A
 State Pit Number 71-3
 Quarry Calcite
 Sample from stockpile at Bay Aggregate
 Pile Location Loading Face

| Sieve Size | Retained Weight | Retained Percent | Cumulative % Retained | Cumulative % Passing | Specification Requirements |
|------------|-----------------|------------------|-----------------------|----------------------|----------------------------|
| 2 1/2 " | | | | | |
| 2 " | | | | | |
| 1 1/2 " | 0 | 0.0% | 0.0% | 100% | |
| 1 1/4 " | | | | | |
| 1 " | 0 | 0.0% | 0.0% | 100% | |
| 3/4 " | 0 | 0.0% | 0.0% | 100% | |
| 1/2 " | 4 | 0.2% | 0.2% | 100% | 100% |
| 3/8 " | 125 | 5.2% | 5.4% | 95% | 95 - 100% |
| no. 4 | 1301 | 54.2% | 59.6% | 40% | 35-65% |
| no. 8 | 806 | 33.6% | 93.2% | 7% | 0-25% |
| no. 16 | 86 | 3.6% | 96.8% | 3% | |
| no. 30 | 38 | 1.6% | 98.4% | 2% | |
| no. 50 | 18 | 0.7% | 99.1% | 1% | |
| no. 100 | 8 | 0.3% | 99.4% | 1% | |
| no. 200 | 9 | 0.4% | 99.8% | 0% | |
| pan | 4 | 0.2% | 100.0% | 0% | 0% |
| LBW | 0 | 0.0% | | | |
| TOTAL: | 2398.20 | 100.00% | | | |

0.00
LOSS BY WASH **LBW MAX**

Initial Weight g
 Weight after Washing g Accepted _____
 Loss by Washing g Rejected _____

MOISTURE
 Initial Weight g Rodded _____
 Dry Weight g Shoveled _____
 Moisture g

Tested By _____

L. Philippi
 Michigan Certified Aggregate Technician
 Cert # 101992-0213